


# Ascot Blend

Size	65mm
Water Absorption	16%
Compressive Strength	7.5 N/mm <sup>2</sup>
Durability	F2
Bricks per pack	600
Pack Weight	1.39T
Salt Classification	S2
Dimensional Tolerance	T2
Dimensional Range	R1



Facebook: traditionalbrick  
LinkedIn: Traditional Brick & Stone  
Instagram: tbsbrick  
Pinterest: tradbrick

[www.traditionalbrickandstone.co.uk](http://www.traditionalbrickandstone.co.uk)

Traditional Brick & Stone Ltd  
Park View House  
Bow Street  
Rugeley  
Staffs  
WS15 2DG

T: 01889 574466 F: 01889227438  
[sales@traditionalbrickandstone.co.uk](mailto:sales@traditionalbrickandstone.co.uk)